

## Cheng Yu Plastic A707G25 SAN, 25% Glass Fiber

Category : Polymer , Thermoplastic , SAN Polymer , Styrene Acrylonitrile (SAN), Molded, Glass Reinforced

Material Notes:

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Cheng-Yu-Plastic-A707G25-SAN-25-Glass-Fiber.php](http://www.lookpolymers.com/polymer_Cheng-Yu-Plastic-A707G25-SAN-25-Glass-Fiber.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.17 g/cc	1.17 g/cc	ASTM D792
Linear Mold Shrinkage	0.0010 - 0.0030 cm/cm	0.0010 - 0.0030 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	93.5	93.5	ASTM D785
Tensile Strength, Yield	141 MPa	20500 psi	ASTM D638
Flexural Yield Strength	196 MPa	28400 psi	ASTM D790
Izod Impact, Notched	0.603 J/cm	1.13 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	111 °C	232 °F	ASTM D648
Flammability, UL94	HB	HB	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China