

Cheng Yu Plastic A778 Electric Resisting ABS

Category : Polymer , Thermoplastic , ABS Polymer

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Cheng-Yu-Plastic-A778-Electric-Resisting-ABS.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.04 g/cc	1.04 g/cc	ASTM D792
Linear Mold Shrinkage	0.0030 - 0.0060 cm/cm	0.0030 - 0.0060 in/in	ASTM D955
Melt Index of Compound	4.0 - 6.0 g/10 min	4.0 - 6.0 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	101	101	ASTM D785
Tensile Strength, Yield	39.0 MPa	5660 psi	ASTM D638
Flexural Yield Strength	98.1 MPa	14200 psi	ASTM D790
Izod Impact, Notched	3.92 J/cm	7.35 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	90.0 °C	194 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China