

Cheng Yu Plastic PP238G3 Polypropylene, 30% Glass Fiber

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 30% Glass Fiber Filler

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Cheng-Yu-Plastic-PP238G3-Polypropylene-30-Glass-Fiber.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.30 g/cc	1.30 g/cc	ASTM D792
Linear Mold Shrinkage	0.015 - 0.020 cm/cm	0.015 - 0.020 in/in	ASTM D955
Melt Index of Compound	10 - 15 g/10 min	10 - 15 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	107	107	ASTM D785
Tensile Strength, Yield	63.7 MPa	9250 psi	ASTM D638
Flexural Yield Strength	118 MPa	17100 psi	ASTM D790
Izod Impact, Notched	0.726 J/cm	1.36 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	143 °C	289 °F	ASTM D648
Flammability, UL94	HB	HB	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China