

Cheng Yu Plastic T889G2 PBT, 20% Glass Fiber

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), 20% Glass Fiber Filled

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Cheng-Yu-Plastic-T889G2-PBT-20-Glass-Fiber.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.40 g/cc	1.40 g/cc	ASTM D792
Linear Mold Shrinkage	0.0050 - 0.020 cm/cm	0.0050 - 0.020 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	94	94	ASTM D785
Tensile Strength, Yield	93.2 MPa	13500 psi	ASTM D638
Flexural Yield Strength	172 MPa	24900 psi	ASTM D790
Izod Impact, Notched	0.785 J/cm	1.47 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	225 °C	437 °F	ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Dielectric Constant	3.5	3.5	ASTM D150
	@Frequency 60 Hz	@Frequency 60 Hz	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China