

## Chevron Phillips 5102 LDPE Injection Blow Molding Resin (discontinued \*\*)

Category : Polymer , Thermoplastic , Polyethylene (PE) , LDPE , Low Density Polyethylene (LDPE), Blow Molding Grade

### Material Notes:

Resin Type: Homopolymer  
Characteristics: Good Core Pin Release, Good Stability, Low Taste and Odor Characteristics, Good Impact and Toughness, Good Clarity on Gloss  
Applications: Squeeze Bottles, Personal Care, Flexible Toys, Adhesives, Toiletries, Food and Drink Bottles, Pharmaceuticals. Burn Rate

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Chevron-Phillips-5102-LDPE-Injection-Blow-Molding-Resin-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_Chevron-Phillips-5102-LDPE-Injection-Blow-Molding-Resin-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	0.923 g/cc	0.0333 lb/in <sup>3</sup>	ASTM D1505
Apparent Bulk Density	0.526 g/cc	0.0190 lb/in <sup>3</sup>	ASTM D1895
Melt Flow	2.0 g/10 min @Load 2.16 kg, Temperature 190 °C	2.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D 1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	56	56	ASTM D2240
Tensile Strength, Yield	17.2 MPa	2490 psi	ASTM D638
Elongation at Break	>= 600 %	>= 600 %	ASTM D638
Flexural Modulus	0.185 GPa	26.8 ksi	3 pt. secant. ASTM D790

Thermal Properties	Metric	English	Comments
Vicat Softening Point	102 °C	216 °F	ASTM D1525
Brittleness Temperature	<= -70.0 °C	<= -94.0 °F	ASTM D746

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China