

## Chevron Phillips 5622 LDPE Shrink and Heavy Duty Packaging Film Resin (discontinued \*\*)

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LDPE , Low Density Polyethylene (LDPE), Film Grade

### Material Notes:

Resin Type: Homopolymer  
Characteristics: Excellent Tensile and Impact Strength, Very Good Abrasion and Tear Resistance, Excellent Retention of Properties after Aging, Wide Range of Shrinkage Characteristics, No Slip and Low Antiblock  
Applications: Pallet Shrink, Heavy Duty Packaging  
Processing Conditions: Extruder 6.35 cm. Screw L/D Ratio 24:1. Die Opening 0.0762 cm. Blow-Up Ratio 2:1. Film properties below based on film thickness of 31.8 µm. Data provided by Chevron Chemical.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Chevron-Phillips-5622-LDPE-Shrink-and-Heavy-Duty-Packaging-Film-Resin-nbspdiscontinued.php](http://www.lookpolymers.com/polymer_Chevron-Phillips-5622-LDPE-Shrink-and-Heavy-Duty-Packaging-Film-Resin-nbspdiscontinued.php)

Physical Properties	Metric	English	Comments
Density	0.923 g/cc	0.0333 lb/in <sup>3</sup>	ASTM D1505
Melt Flow	0.50 g/10 min	0.50 g/10 min	Condition E; ASTM D 1238

Mechanical Properties	Metric	English	Comments
Secant Modulus, MD	0.170 GPa	24.7 ksi	ASTM D882
Secant Modulus, TD	0.180 GPa	26.1 ksi	ASTM D882
Coefficient of Friction	0.50	0.50	ASTM D1894
Dart Drop	2.80 g/micron	71.1 g/mil	F <sub>&gt;50</sub> ; 1.5 in. dart/26 in. drop height; ASTM D 1709

Optical Properties	Metric	English	Comments
Haze	7.0 %	7.0 %	ASTM D2457
Gloss	57 %	57 %	at 45°. ASTM D 2457
	90 %	90 %	at 60°. ASTM D 2457

Processing Properties	Metric	English	Comments
Melt Temperature	204 °C	399 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China