

Chevron Phillips HiD® 9302 HDPE Yellow Pipe Resin (discontinued **)

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Pipe Grade

Material Notes:

Resin Type: Linear Copolymer; PE2406 Pipe Resin; ASTM D 3350 Classification: 234363E; ASTM D 4976 Classification: PE 225, A 56607 Applications: Natural Gas Distribution Piping and Fittings Data provided by Chevron Chemical.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chevron-Phillips-HiD-9302-HDPE-Yellow-Pipe-Resin-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.940 g/cc	0.0340 lb/in ³	ASTM D1505
Environmental Stress Crack Resistance	>= 2000 hour @Temperature 50.0 °C	>= 2000 hour @Temperature 122 °F	F ₅₀ , Cond. B.; ASTM D1693
	>= 5000 hour @Temperature 100 °C	>= 5000 hour @Temperature 212 °F	F ₅₀ Cond. C; ASTM D1693
Melt Flow	0.20 g/10 min @Load 2.16 kg, Temperature 190 °C	0.20 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D 1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	63	63	ASTM D2240
Tensile Strength, Ultimate	31.0 MPa	4500 psi	ASTM D638
Tensile Strength, Yield	19.0 MPa	2760 psi	ASTM D638
Elongation at Break	>= 800 %	>= 800 %	ASTM D638
Flexural Modulus	0.790 GPa	115 ksi	3 pt. secant. ASTM D790

Thermal Properties	Metric	English	Comments
Vicat Softening Point	120 °C	248 °F	ASTM D1525
Brittleness Temperature	<= -59.0 °C	<= -74.2 °F	ASTM D746

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China