

Chevron Phillips HiD® 9308 HDPE Natural Pipe Resin (discontinued **)

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Pipe Grade

Material Notes:

Resin Type: Linear Copolymer; PE3408 Pipe Resin; ASTM D 3350 Classification: 345460A; ASTM D 4976 Classification: PE 235, A 56607
 Applications: Base Resin for use in Oil Patch and Industrial Pipe Applications
 Data provided by Chevron Chemical.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chevron-Phillips-HiD-9308-HDPE-Natural-Pipe-Resin-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.9445 g/cc	0.03412 lb/in ³	ASTM D1505
Environmental Stress Crack Resistance	>= 1500 hour @Temperature 50.0 °C	>= 1500 hour @Temperature 122 °F	F ₅₀ , Cond. B.; ASTM D1693
	>= 1500 hour @Temperature 100 °C	>= 1500 hour @Temperature 212 °F	F ₅₀ Cond. C; ASTM D1693
High Load Melt Index	9.0 g/10 min @Load 21.6 kg, Temperature 190 °C	9.0 g/10 min @Load 47.6 lb, Temperature 374 °F	High Load; ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	66	66	ASTM D2240
Tensile Strength, Ultimate	34.0 MPa	4930 psi	ASTM D638
Tensile Strength, Yield	23.0 MPa	3340 psi	ASTM D638
Elongation at Break	>= 800 %	>= 800 %	ASTM D638
Stiffness Modulus	0.900 GPa	131 ksi	3 pt. secant ASTM D790

Thermal Properties	Metric	English	Comments
Vicat Softening Point	126 °C	259 °F	ASTM D1525
Brittleness Temperature	<= -59.0 °C	<= -74.2 °F	ASTM D746

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China