

Chevron Phillips HiD® 9662 HDPE Blown Film Resin (discontinued **)

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Film Grade

Material Notes:

Resin Type: Linear Polyethylene Homopolymer
 Characteristics: Unique Molecular Architecture Gives Outstanding Moisture Barrier Properties, Excellent Film Strength and Toughness for a Homopolymer, Gives Paper-like Film Texture, Embosses Extremely Well, Draws to Very Thin Gauges, Excellent Heat Seal Strength
 Applications: Food Packaging, Coextrusions, Tissue Paper Replacement, Deli Wrap, Moisture Barrier Films.
 Film properties below based on film thickness of 25.4 µm. Data provided by Chevron Chemical.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chevron-Phillips-HiD-9662-HDPE-Blown-Film-Resin-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.962 g/cc	0.0348 lb/in ³	ASTM D1505
Moisture Vapor Transmission	0.100 cc-mm/m ² -24hr-atm	0.254 cc-mil/100 in ² -24hr-atm	ASTM F1249
Melt Flow	1.05 g/10 min	1.05 g/10 min	Condition E; ASTM D 1238

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	490 %	490 %	ASTM D882
Film Elongation at Break, TD	550 %	550 %	ASTM D882
Secant Modulus, MD	1.10 GPa	160 ksi	ASTM D882
Secant Modulus, TD	1.20 GPa	174 ksi	ASTM D882
Elmendorf Tear Strength, MD	0.748 g/micron	19.0 g/mil	Notched; ASTM D1922
Elmendorf Tear Strength, TD	8.27 g/micron	210 g/mil	ASTM D1922
Dart Drop	1.40 g/micron	35.6 g/mil	1.5 in. dart/26 in. drop height; ASTM D 1709
Film Tensile Strength at Break, MD	42.0 MPa	6090 psi	ASTM D882
Film Tensile Strength at Break, TD	26.0 MPa	3770 psi	ASTM D882

Processing Properties	Metric	English	Comments
Melt Temperature	210 °C	410 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China