

Chevron Phillips MarFlex® 7308FK Polyethylene; LLDPE

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LLDPE

Material Notes:

Hexene linear low density polyethylene. This LLDPE is tailored for blown film applications that require: Excellent processability Increased stiffness Good toughness Use alone or in blends with LDPE or HDPE High slip and low antiblocking agents Applications: Typical blown film applications include: Heavy duty bags Industrial packaging Institutional packaging General purpose packaging Information provided by Phillips

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chevron-Phillips-MarFlex-7308FK-Polyethylene-LLDPE.php

Physical Properties	Metric	English	Comments
Density	0.925 g/cc	0.0334 lb/in ³	ASTM D-1505
Melt Index of Compound	0.80 g/10 min @Load 2.16 kg, Temperature 190 °C	0.80 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D-1238

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	400 %	400 %	Blown Film at 1 mil; ASTM D-882
Film Elongation at Break, TD	700 %	700 %	Blown Film at 1 mil; ASTM D-882
Coefficient of Friction	0.15	0.15	Blown Film at 1 mil; ASTM D-1894
Elmendorf Tear Strength, MD	11.8 g/micron	300 g/mil	Blown Film at 1 mil; ASTM D-1922
Elmendorf Tear Strength, TD	25.6 g/micron	650 g/mil	Blown Film at 1 mil; ASTM D-1922
Dart Drop	4.92 g/micron	125 g/mil	Blown Film at 1 mil; ASTM D-1709
Film Tensile Strength at Break, MD	55.0 MPa	7980 psi	Blown Film at 1 mil; ASTM D-882
Film Tensile Strength at Break, TD	34.0 MPa	4930 psi	Blown Film at 1 mil; ASTM D-882
1% Secant Modulus, MD	290 MPa	42000 psi	Blown Film at 1 mil; ASTM D-882
1% Secant Modulus, TD	345 MPa	50000 psi	Blown Film at 1 mil; ASTM D-882

Optical Properties	Metric	English	Comments
Haze	18 %	18 %	Blown Film at 1 mil; ASTM D-1003
Gloss	65 %	65 %	60°, Blown Film at 1 mil; ASTM D-2457

Descriptive Properties	Value	Comments
------------------------	-------	----------

Descriptive Properties

Value

Comments

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China