

## Chevron Phillips MarFlex® 9607 HDPE Cast Film Resin

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Film Grade

**Material Notes:**

Characteristics: Very Low Gel Levels, Produces Very "Clear" Film, Draws to Thin Gauges, Low Taste and Odor Transfer, Excellent MVTR for a Chill Cast Film, Excellent Processability, Excellent Optical Properties Applications: Coextrusions, Overwrap, Food Packaging, Moisture Sensitive Packaging

Film properties below based on film thickness of 31.8 µm. Data provided by Chevron Chemical.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Chevron-Phillips-MarFlex-9607-HDPE-Cast-Film-Resin.php](http://www.lookpolymers.com/polymer_Chevron-Phillips-MarFlex-9607-HDPE-Cast-Film-Resin.php)

Physical Properties	Metric	English	Comments
Density	0.962 g/cc	0.0348 lb/in <sup>3</sup>	ASTM D1505
Moisture Vapor Transmission	0.170 cc-mm/m <sup>2</sup> -24hr-atm	0.432 cc-mil/100 in <sup>2</sup> -24hr-atm	ASTM F1249
Melt Flow	6.5 g/10 min	6.5 g/10 min	Condition E; ASTM D 1238

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	870 %	870 %	ASTM D882
Film Elongation at Break, TD	790 %	790 %	ASTM D882
Secant Modulus, MD	0.760 GPa	110 ksi	ASTM D882
Secant Modulus, TD	0.840 GPa	122 ksi	ASTM D882
Elmendorf Tear Strength, MD	1.38 g/micron	35.0 g/mil	Notched; ASTM D1922
Elmendorf Tear Strength, TD	3.94 g/micron	100 g/mil	ASTM D1922
Dart Drop	1.30 g/micron	33.0 g/mil	1.5 in. dart/26 in. drop height; ASTM D 1709
Film Tensile Strength at Break, MD	29.0 MPa	4210 psi	ASTM D882
Film Tensile Strength at Break, TD	23.0 MPa	3340 psi	ASTM D882

Optical Properties	Metric	English	Comments
Haze	11 %	11 %	ASTM D2457
Gloss	120 %	120 %	at 60°. ASTM D 2457

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China