

## Chevron Phillips Marlex® 1003 LDPE Injection Molding Resin

Category : Polymer , Thermoplastic , Polyethylene (PE) , LDPE , Low Density Polyethylene (LDPE), Molded

### Material Notes:

Resin Type: Homopolymer  
Characteristics: Excellent flexibility  
Excellent flow  
Moderate mold release  
Good warpage resistance  
Applications: Housewares  
Tampers evident, snap-on caps  
Wine bottle sleeve caps  
Information provided by Chevron Phillips.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Chevron-Phillips-Marlex-1003-LDPE-Injection-Molding-Resin.php](http://www.lookpolymers.com/polymer_Chevron-Phillips-Marlex-1003-LDPE-Injection-Molding-Resin.php)

Physical Properties	Metric	English	Comments
Density	0.917 g/cc	0.0331 lb/in <sup>3</sup>	ASTM D1505
Melt Index of Compound	13 g/10 min	13 g/10 min	Condition 190/2.16; ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	46	46	ASTM D2240
Tensile Strength, Yield	9.00 MPa	1310 psi	2 in/min, Type IV bar; ASTM D638
Elongation at Break	550 %	550 %	2 in/min, Type IV bar; ASTM D638
Flexural Modulus	0.200 GPa	29.0 ksi	Tangent, 16:1 span:depth, 0.5in/min; ASTM D790

Thermal Properties	Metric	English	Comments
Vicat Softening Point	86.0 °C	187 °F	Loading 1, Rate A; ASTM D1525
Brittleness Temperature	-52.0 °C	-61.6 °F	Type A, type 1 specimen; ASTM D746

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China