

Chevron Phillips Marlex® 4538A LDPE Blow Molding Resin

Category : Polymer , Thermoplastic , Polyethylene (PE) , LDPE , Low Density Polyethylene (LDPE), Blow Molding Grade

Material Notes:

Resin Type: Homopolymer
Characteristics: High Melt Strength, Good Parison Control, Good Stability, Low Taste and Odor Characteristics, Good Impact and Toughness, Good Clarity on Gloss, Long Standing in the Pharmaceutical Industry
Applications: Squeeze Bottles, Personal Care, Flexible Toys, Adhesives, Toiletries, Food and Drink Bottles, Pharmaceuticals. Burn Rate

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chevron-Phillips-Marlex-4538A-LDPE-Blow-Molding-Resin.php

Physical Properties	Metric	English	Comments
Density	0.925 g/cc	0.0334 lb/in ³	ASTM D1505
Apparent Bulk Density	0.526 g/cc	0.0190 lb/in ³	ASTM D1895
Melt Flow	2.0 g/10 min @Load 2.16 kg, Temperature 190 °C	2.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D 1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	56	56	ASTM D2240
Tensile Strength, Yield	17.2 MPa	2490 psi	ASTM D638
Elongation at Break	>= 600 %	>= 600 %	ASTM D638
Flexural Modulus	0.185 GPa	26.8 ksi	3 pt. secant. ASTM D790

Thermal Properties	Metric	English	Comments
Vicat Softening Point	102 °C	216 °F	ASTM D1525
Brittleness Temperature	<= -70.0 °C	<= -94.0 °F	ASTM D746

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China