

## Chevron Phillips Marlex® HHM TR-480XC HDPE Pipe and Corrugated Extrusion Resin (discontinued \*\*)

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Extruded

### Material Notes:

Characteristics: Good long-term hoop strength performance Very high melt strength > Outstanding low temperature toughness Applications: Municipal, industrial, and mining pipe Oil and gas gathering pipe Information provided by Chevron Phillips.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Chevron-Phillips-Marlex-HHM-TR-480XC-HDPE-Pipe-and-Corrugated-Extrusion-Resin-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_Chevron-Phillips-Marlex-HHM-TR-480XC-HDPE-Pipe-and-Corrugated-Extrusion-Resin-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	0.955 g/cc	0.0345 lb/in <sup>3</sup>	ASTM D1505
Melt Flow	11 g/10 min	11 g/10 min	Condition 190/2.16, HLMI; ASTM D1238

Mechanical Properties	Metric	English	Comments
PENT	>= 100 hour	>= 100 hour	Slow crack growth; ASTM F1473
Tensile Strength, Yield	22.0 MPa	3190 psi	2 in/min, Type IV bar; ASTM D638
Elongation at Break	800 %	800 %	2 in/min, Type IV bar; ASTM D638
Flexural Modulus	0.760 GPa	110 ksi	2% Secant; ASTM D3350
Hydrostatic Design Basis	5.50 MPa	798 psi	60°C; ASTM D2837
	11.0 MPa	1600 psi	ASTM D2837
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Brittleness Temperature	<= -75.0 °C	<= -103 °F	Type A clamp, type 1 specimen; ASTM D746

Descriptive Properties	Value	Comments
Minimum Required Strength	8 MPa	ISO 9080

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China