

Chevron Phillips Marlex® HMN TR-942/942G Polyethylene; HDPE

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE

Material Notes:

High density polyethylene. These hexene copolymers are tailored for rotational molding applications that require: Wide process windows and fair flow Long-term UV stabilization Excellent impact strength Good ESCR These resins are available in: Pellet form - HMN TR-94235 US mesh powder - HMN TR-942G Applications: Potable water and chemical tanks Agricultural equipment Information provided by Phillips These resins meet the following specifications: ASTM D4976 - PE 233 FDA 21 CFR 177.1520(c) 3.2a, use conditions B through H per 21 CFR 176.170(c) Table 2. Single use articles contacting food types I, II, IV-B, VI-A, VI-B, VII-B, and VIII. Repeated use articles contacting all food types defined in 21 CFR 176.170(c) Table 1.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chevron-Phillips-Marlex-HMN-TR-942942G-Polyethylene-HDPE.php

Physical Properties	Metric	English	Comments
Density	0.943 g/cc	0.0341 lb/in ³	ASTM D-1505
ESCR 100% Igepal®	700 hour	700 hour	Condition A, F50; ASTM D-1693
ESCR 10% Igepal®	250 hour	250 hour	Condition A, F50; ASTM D-1693
Melt Index of Compound	2.0 g/10 min @Load 2.16 kg, Temperature 190 °C	2.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D-1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	61	61	ASTM D-2240
Tensile Strength, Yield	21.0 MPa	3050 psi	2 in/min, Type IV bar; ASTM D-638
Elongation at Break	720 %	720 %	2 in/min, Type IV bar; ASTM D-638
Flexural Modulus	0.720 GPa	104 ksi	2% Secant - 16:1 span:depth, 0.5 in/min; ASTM D-790
	0.860 GPa	125 ksi	Tangent - 16:1 span:depth, 0.5 in/min; ASTM D-790
Impact Test	92.0 J @Thickness 3.17 mm, Temperature -40.0 °C	67.9 ft-lb @Thickness 0.125 in, Temperature -40.0 °F	ARM Impact
	244 J @Thickness 6.35 mm, Temperature -40.0 °C	180 ft-lb @Thickness 0.250 in, Temperature -40.0 °F	ARM Impact

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Melting Point Thermal Properties	130 °C Metric	266 °F English	ASTM D-3418 Comments
Crystallization Temperature	113 °C	235 °F	ASTM D-3418
Deflection Temperature at 0.46 MPa (66 psi)	64.0 °C	147 °F	Method A; ASTM D-648
Deflection Temperature at 1.8 MPa (264 psi)	44.0 °C	111 °F	Method A; ASTM D-648
Vicat Softening Point	120 °C	248 °F	Loading 1, Rate A; ASTM D-1525
Brittleness Temperature	-75.0 °C	-103 °F	Type A, Type I specimen; ASTM D-746

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China