

ChevronTexaco ATF+3® Automatic Transmission Fluid

Category: Fluid, Lubricant

Material Notes:

General DescriptionDaimlerChrysler has had their own ATF specifications for many years, but as of 1997, Chrysler owners manuals no longer list DEXRON as an acceptable replacement. ATF+3 is a readily available mineral oil-based ATF that is suitable in any application calling for ATF PLUS®, ATF+2®, or a Type 7176® fluid. Vehicles manufactured after 1999 require ATF+4®, a synthetic-based ATF only available through DaimlerChrysler. Chevron ATF+3 is specially formulated to optimize performance of Chrysler transmissions and transaxles. Applications Chevron ATF+3 Automatic Transmission Fluid is designed for use in all Chrysler automatic transmissions and automatic transaxles where a Mopar ATF PLUS, ATF+2 or ATF+3 fluid is specified. It is not recommended for use in transmissions specifying either DEXRON® or MERCON® type fluids Chevron ATF+3 Automatic Transmission Fluid has been registered with the Chrysler Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ChevronTexaco-ATF3-Automatic-Transmission-Fluid.php

| Physical Properties | Metric | English | Comments |
|--------------------------------------|-----------------------|-----------------------|-----------------------------|
| API Gravity | 31.2° | 31.2° | |
| Brookfield Viscosity | 18000 cP | 18000 cP | |
| | @Temperature -40.0 °C | @Temperature -40.0 °F | |
| Viscosity Measurement | 188 | 188 | Viscosity Index; ASTM D2270 |
| Kinematic Viscosity at 40°C (104°F) | 35.9 cSt | 35.9 cSt | ASTM D445 |
| Kinematic Viscosity at 100°C (212°F) | 7.6 cSt | 7.6 cSt | ASTM D445 |

| Thermal Properties | Metric | English | Comments |
|--------------------|----------|----------|----------|
| Pour Point | -48.0 °C | -54.4 °F | ASTM D97 |
| Flash Point | 194 °C | 381 °F | ASTM D92 |

| Descriptive Properties | Value | Comments |
|------------------------|-------|----------|
| Color | Red | |

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China