

ChevronTexaco Coupling Grease

Category : Fluid , Lubricant , Lithium Gellant

Material Notes:

FeaturesChevron Coupling Grease is a brown, stringy and tacky grease manufactured using a high viscosity base oil, a lithium soap thickener, rust and oxidation inhibitors, and extreme pressure and polymer tackiness additives. It is designed for all high-speed grease lubricated flexible couplings and is specially formulated to provide specific resistance to centrifugal separation in highspeed gear or grid couplings. Chevron Coupling Grease has high load-carrying capacity and therefore provides good protection of lubricated parts against wear. **Applications**Chevron Coupling Grease is specifically designed for the lubrication of high-speed grease lubricated flexible couplings where high centrifugal forces are present. It is recommended for use in high-speed grid, gear, or chain couplings in a variety of industrial applications. Chevron Coupling Grease meets the coupling requirements of AGMA CG-1 and CG-2 type couplings. Chevron Coupling Grease exhibits little to no oil separation in the ASTM D4425 high-speed centrifuge test.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ChevronTexaco-Coupling-Grease.php

Physical Properties	Metric	English	Comments
Kinematic Viscosity at 100°C (212°F)	250 cSt	250 cSt	ASTM D445

Mechanical Properties	Metric	English	Comments
Four Ball Extreme Pressure, Weld Load	250 kg	551 lb (mass)	Weld Point
Penetration	336	336	Worked
Penetration P(0), 1/10 mm	252	252	
Timken Test	18100 g	40.0 lb	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	138 °C	280 °F	
Minimum Service Temperature, Air	0.000 °C	32.0 °F	
Dropping Point	215 °C	419 °F	

Descriptive Properties	Value	Comments
Color	Brown	
Texture	Tacky	
Thickener, % / type	5 / Lithium	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China