

## ChevronTexaco ECO® SAE 10W-30 Motor Oil

Category: Fluid, Lubricant

## **Material Notes:**

FeaturesChevron ECO Motor Oil is formulated to be an environmentally responsible engine lubricant. It uses the highest quality re-refined base oils and special additives to protect against high temperature oxidation, wear, and viscosity breakdown. It is additionally fortified with a detergent dispersant and rust and corrosion inhibitors to keep engines clean and free from sludge, varnish, and rust. Applications Chevron ECO Motor Oil is recommended for all four-stroke gasoline engines used in passenger cars, light trucks, and powerboats, including those equipped with superchargers and turbochargers. It is specifically recommended for turbocharged and small displacement, high rpm gasoline engines. These engines experience higher operating temperatures and require a motor oil that provides maximum protection against both viscosity and thermal breakdown. Chevron ECO Motor Oil is a high performance oil designed to meet the latest API category. Chevron ECO Motor Oil is qualified for API Service Categories SJ, SH, SG.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_ChevronTexaco-ECO-SAE-10W-30-Motor-Oil.php

Physical Properties	Metric	English	Comments	
API Gravity	30.1 °	30.1 °		
Viscosity	2900 cP	2900 cP	Cold Crank	
Viscosity	@Temperature -20.0 °C	@Temperature -4.00 °F	Colu Clarik	
Viscosity Measurement	156	156	Viscosity Index; ASTM D2270	
Kinematic Viscosity at 40°C (104°F)	59 cSt	59 cSt	ASTM D445	
Kinematic Viscosity at 100°C (212°F)	10.8 cSt	10.8 cSt	ASTM D445	
Ash	0.67 %	0.67 %	Sulfated Ash wt%	

Thermal Properties	Metric	English	Comments
Pour Point	-33.0 °C	-27.4 °F	ASTM D97
Flash Point	222 °C	432 °F	ASTM D92

Component Elements Properties	Metric	English	Comments
Phosphorous, P	0.096 %	0.096 %	
Zinc, Zn	0.101 %	0.101 %	

Chemical Properties	Metric	English	Comments
Total Base Number	7.7	7.7	ASTM D2896



Descriptive Properties	Value	Comments
Re-refined Oil Content, % of Base Oil	68	

## **Contact Songhan Plastic Technology Co.,Ltd.**

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China