## ChevronTexaco ECO® SAE 30 Heavy Duty Motor Oil

Category : Fluid , Lubricant

#### Material Notes:

Features:Chevron ECO Heavy Duty Motor Oils are formulated to be environmentally responsible engine lubricants. They use the highest quality re-refined base oils and specially selected additives designed to provide excellent performance in all recommended applications.They contain an effective detergent dispersant to keep sulfated ash to a minimum. They are fortified with oxidation and corrosion inhibitors, high temperature antiwear additives, and foam inhibitors to protect vital engine parts from scuffing and protect the bearings from corrosion.Chevron ECO Heavy Duty Motor Oil SAE 15W-40 is designed to meet the warranty requirements of most manufacturers of diesel engines. The high alkaline reserve (base number) effectively protects bearings and other engine surfaces from the corrosive effect of acids formed by the combustion of high sulfur fuels.ApplicationsChevron ECO Heavy Duty Motor Oils:exceed the requirements of Caterpillar Series 3 and are recommended when the sulfur content of the fuel is unknown or exceeds 0.50%.exceed the Mack EO K/2 specification. Mack's preferred recommendation is SAE 15W-40.meet and exceed service requirements for Cummins and Detroit Diesel engines when recommending these viscosity grades.are recommended for all turbocharged engines where the manufacturer specified a Caterpillar Series 3 oil. are not recommended for Electro Motive Diesel engines with silver bearings. can also be used in gasoline passenger cars and light trucks.

### Order this product through the following link:

http://www.lookpolymers.com/polymer\_ChevronTexaco-ECO-SAE-30-Heavy-Duty-Motor-Oil.php

Physical Properties	Metric	English	Comments
API Gravity	28.6 °	28.6 °	
Viscosity Measurement	104	104	Viscosity Index; ASTM D2270
Kinematic Viscosity at 40°C (104°F)	108.6 cSt	108.6 cSt	ASTM D445
Kinematic Viscosity at 100°C (212°F)	12.3 cSt	12.3 cSt	ASTM D445
Ash	1.2 %	1.2 %	Sulfated Ash wt%

Thermal Properties	Metric	English	Comments
Pour Point	-18.0 °C	-0.400 °F	ASTM D97
Flash Point	232 °C	450 °F	ASTM D92

Component Elements Properties	Metric	English	Comments	
Phosphorous, P	0.10 %	0.10 %		
Zinc, Zn	0.11 %	0.11 %		

Chemical Properties	Metric	English	Comments
Total Base Number	8.0	8.0	ASTM D2896

## SONGHAN Plastic Technology Co., Ltd.

Chemical Properties	Metric	English	Comments	
Descriptive Properties			Value	Comments
Re-refined Oil Content, % of Base Oil			100	

# Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China