

ChevronTexaco HiPerSYN™ ISO 68 Oil

Category : Fluid , Lubricant

Material Notes:

Features Chevron HiPerSYN Oils are synthetic compressor, bearing, and gear oils. They provide outstanding thermal and oxidation stability, high viscosity index, high flash point, low pour point, and excellent hydrolytic stability. Chevron HiPerSYN Oils protect against rust, oxidation, and foaming, and have good antiwear properties. The natural thermal and oxidation stability of these lubricants, due to their high level of purity and refinement, has been further enhanced by their unique additive systems. The high thermal and oxidation stability reduces the formation of oxidation byproducts and acidic materials which will eventually cause deposits and varnish. They are able to withstand relatively high temperature operations for extended periods of time. They have very good demulsibility characteristics allowing quick release of moisture. They minimize entrained air, which could otherwise result in reduced lubricant film thickness and potentially lead to pump cavitation. Chevron HiPerSYN Oils pass the acute aquatic toxicity (LC-50) criteria adopted by the U.S. Fish and Wildlife Service and the U.S. Environmental Protection Agency (EPA). Chevron HiPerSYN Oils are registered with NSF and are acceptable as a lubricant where there is no possibility of food contact (H2) in and around food processing areas. The NSF Nonfood Compounds Registration Program is a continuation of the USDA product approval and listing program, which is based on meeting regulatory requirements of appropriate use, ingredient review and labeling verification. Applications Chevron HiPerSYN Oils are formulated to provide outstanding lubricating qualities for air compressors, especially portable and stationary rotary, vane, and screw compressors. Chevron HiPerSYN Oils are recommended for industrial bearings and gears, such as worm gears, that require an R&O type synthetic gear oil. Chevron HiPerSYN Oils are designed for applications with wide operating temperature ranges. They are especially effective in high temperature applications, like sootblowers, where outstanding thermal and oxidative stability are required. Do not use in high pressure systems in the vicinity of flames, sparks and hot surfaces. Use only in well ventilated areas. Keep container closed. Do not use in breathing air apparatus or medical equipment.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ChevronTexaco-HiPerSYN-ISO-68-Oil.php

Physical Properties	Metric	English	Comments
API Gravity	35.9 °	35.9 °	
Viscosity Measurement	150	150	Viscosity Index; ASTM D2270
Saybolt Viscosity at 100°F	330 SUS	330 SUS	
Saybolt Viscosity at 210°F	61.7 SUS	61.7 SUS	
Kinematic Viscosity at 40°C (104°F)	64.6 cSt	64.6 cSt	ASTM D445
Kinematic Viscosity at 100°C (212°F)	10.4 cSt	10.4 cSt	ASTM D445
Oxidative Stability	30 hour	30 hour	25 psi pressure drop; ASTM D2272
	>= 18000 hour	>= 18000 hour	Hours to 2.0 mg KOH/g acid number; ASTM D943

Mechanical Properties	Metric	English	Comments
Four Ball Wear	0.410 mm	0.0161 in	1800 rpm

Mechanical Properties	Metric	English	Comments
Thermal Properties	Metric	English	Comments
Pour Point	-42.0 °C	-43.6 °F	ASTM D97
Flash Point	254 °C	489 °F	ASTM D92

Descriptive Properties	Value	Comments
Color	L 0.5	
Corrosion, Copper Strip Test 3h	1B	
Foaming Stability, mL	0	
Foaming Tendency Sequence I	10	
Water Separability, Minutes to 0 mL emulsion	15	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China