

ChevronTexaco Marfak® Heavy Duty 2

Category : Fluid , Lubricant , Organic Soap Gellant

Material Notes:

Texaco Marfak grease delivers value through: Good film strength Good rust and corrosion protection, even in wet conditions. Texaco Marfak greases are fibrous sodium soap greases. It resists oil separation and protects against dirt and rust. Texaco Marfak grease is formulated to: Protect equipment from dust and dirt by providing a seal Protect equipment against rusting in the presence of small amounts of water. Texaco Marfak grease is recommended for slow speed, plain bearing and general-purpose lubrication of agricultural equipment. Typical test data are average values only. Minor variations which do not affect product performance are to be expected in normal manufacturing. Notes: Minimum operating temperature is the lowest temperature at which a grease, already in place, could be expected to provide lubrication. Most greases cannot be pumped at these minimum temperatures. Maximum operating temperature is the highest temperature at which the grease could be used with frequent (daily) relubrication. Determined on mineral oil extracted by vacuum filtration. CPS Number: 221981; MSDS Number: 9004

Order this product through the following link:

http://www.lookpolymers.com/polymer_ChevronTexaco-Marfak-Heavy-Duty-2.php

Physical Properties	Metric	English	Comments
Saybolt Viscosity at 100°F	1572 SUS	1572 SUS	See Note 3.
Saybolt Viscosity at 210°F	90 SUS	90 SUS	See Note 3.
Kinematic Viscosity at 40°C (104°F)	290 cSt	290 cSt	See Note 3.
Kinematic Viscosity at 100°C (212°F)	17.5 cSt	17.5 cSt	See Note 3.

Mechanical Properties	Metric	English	Comments
Penetration P(60), 1/10 mm	280	280	Unknown Amount of Work, 25°C (77°F)
Oil Separation	0.20 %	0.20 %	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	135 °C	275 °F	See Note 2.
Minimum Service Temperature, Air	29.0 °C	84.2 °F	See Note 1.
Flash Point	220 °C	428 °F	See Note 3.
Dropping Point	182 °C	360 °F	

Descriptive Properties	Value	Comments
Color	Brown	
Rust Prevention	Pass	

Descriptive Properties Texture	Value Fibrous	Comments
Thickener, %	13	Sodium

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China