

## ChevronTexaco Multifak® AFB NLGI Grade 2

Category : Fluid , Lubricant , Lithium Gellant

## Material Notes:

Typical test data are average values only. Minor variations which do not affect product performance are to be expected in normal manufacturing. Notes: Minimum operating temperature is the lowest temperature at which a grease, already in place, could be expected to provide lubrication. Most greases cannot be pumped at these minimum temperatures. Maximum operating temperature is the highest temperature at which the grease could be used with frequent (daily) relubrication. Determined on mineral oil extracted by vacuum filtration. Unknown amount of work. CPS Number: 220940; MSDS Number: 8963

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ChevronTexaco-Multifak-AFB-NLGI-Grade-2.php](http://www.lookpolymers.com/polymer_ChevronTexaco-Multifak-AFB-NLGI-Grade-2.php)

Physical Properties	Metric	English	Comments
Saybolt Viscosity at 100°F	240 SUS	240 SUS	See Note 3.
Saybolt Viscosity at 210°F	51 SUS	51 SUS	See Note 3.
Kinematic Viscosity at 40°C (104°F)	48 cSt	48 cSt	See Note 3.
Kinematic Viscosity at 100°C (212°F)	7.3 cSt	7.3 cSt	See Note 3.

Mechanical Properties	Metric	English	Comments
Penetration	5.0	5.0	% Change, (10000X), 25°C, See Note 4.
Penetration P(60), 1/10 mm	280	280	Unknown Amount of Work, 25°C (77°F)

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	121 °C	250 °F	See Note 2.
Minimum Service Temperature, Air	-40.0 °C	-40.0 °F	See Note 1.
Pour Point	-12.0 °C	10.4 °F	See Note 3.
Flash Point	200 °C	392 °F	See Note 3.
Dropping Point	188 °C	370 °F	

Descriptive Properties	Value	Comments
Color	Brown	
Texture	Smooth	
Thickener, %	8	Lithium

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China