

## ChevronTexaco Open Gear Grease

Category : Fluid , Lubricant

### Material Notes:

Features Chevron Open Gear Greases are formulated with high viscosity mineral oils in a nonsoap-based thickener. These greases appear brownish-black and are extremely tacky. Chevron Open Gear Greases contain special functional fillers such as molybdenum disulfide and graphite, which impart a long-lasting film on working surfaces. They also contain tackiness additives, wetting agents and rust inhibitors to protect metal surfaces. None of the Chevron Open Gear Greases contain chlorinated solvents. Chevron Open Gear Greases have been formulated with a diluent that does not require a cancer warning label. Chevron Open Gear Greases are in every sense true greases and not asphalt-based open gear lubricants. This has a number of advantages. The lubricants can carry a more complete additive system including friction modifiers such as molybdenum disulfide and graphite, which apply a long lasting antiwear film on gear teeth. Applications Chevron Open Gear Greases are recommended: for all open gears in industrial, mining, construction, and marine equipment for chain and sprocket lubrication as a tenacious fifth wheel lubricant Chevron Open Gear Greases can be applied in a variety of methods, including: from a cartridge in a caulking gun from an aerosol can for easy application in hard-to-reach lubrication points through a mechanical lubricator over a wide range of operating temperatures

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ChevronTexaco-Open-Gear-Grease.php](http://www.lookpolymers.com/polymer_ChevronTexaco-Open-Gear-Grease.php)

Physical Properties	Metric	English	Comments
Kinematic Viscosity at 40°C (104°F)	6532 cSt	6532 cSt	ASTM D445
Kinematic Viscosity at 100°C (212°F)	152 cSt	152 cSt	ASTM D445

Mechanical Properties	Metric	English	Comments
Four Ball Extreme Pressure, Weld Load	315 kg	695 lb (mass)	
Four Ball Wear	0.600 mm	0.0236 in	
Penetration P(0), 1/10 mm	375	375	

Thermal Properties	Metric	English	Comments
Flash Point	204 °C	399 °F	ASTM D92

Descriptive Properties	Value	Comments
Color	Brown-Black	
Resultant Film	Tacky	
Rust Test, ASTM D1743, rating	Pass	
Texture	Smooth	

Thickener % / type Descriptive Properties	Nonsoap Value	Comments
--	------------------	----------

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China