

## ChevronTexaco ParaLux® 701R Process Oil

Category : Fluid , Lubricant

### Material Notes:

**Features** PARALUX is produced using an all-hydroprocessing route which transforms the molecular structure of undesirable aromatics into highly desirable saturates. This produces a process oil with superior physical and chemical properties :lower aromatics result in superior color stability.Lower volatility improves efficiency.Excellent compatibility with rubber polymers reduces processing headaches.**Applications** Because PARALUX is produced by all-hydroprocessing, it has performance properties that surpass most conventional paraffinic process oils and approach or surpass many of the performance characteristics of technical white oils. These advantages include:Exceptionally low aromatic contentBetter color and UV stability than conventional paraffinic or naphthenic oilsAlmost complete resistance to degradation from ultraviolet discolorationLower volatility results in fewer emissions, so less make-up oil is needed and costs are minimizedExcellent compatibility with rubber polymers which require paraffinic oils. Only all-hydroprocessed oils can deliver all of these advantagesChevron ParaLux Process Oils are ideal for use in compounding a wide variety of products, including :FootwearWire and Cable insulationAdhesives, sealants and coatingsPolymer modified asphaltsAutomobile interior moldingsAutomotive under hood partsTires, tire whitewalls, tubes, and inner linersRubber membranesWeather Stripping

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ChevronTexaco-ParaLux-701R-Process-Oil.php](http://www.lookpolymers.com/polymer_ChevronTexaco-ParaLux-701R-Process-Oil.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.8509 g/cc	0.8509 g/cc	
API Gravity	34.8 °	34.8 °	
Viscosity Measurement	0.8112	0.8112	Viscosity Gravity Constant
Saybolt Viscosity at 100°F	70 SUS	70 SUS	
Saybolt Viscosity at 210°F	36 SUS	36 SUS	
Kinematic Viscosity at 40°C (104°F)	12.1 cSt	12.1 cSt	ASTM D445
Kinematic Viscosity at 100°C (212°F)	2.9 cSt	2.9 cSt	ASTM D445
Molecular Weight	318 g/mol	318 g/mol	ASTM D2502

Thermal Properties	Metric	English	Comments
Pour Point	-40.0 °C	-40.0 °F	ASTM D97
Flash Point	81.7 °C	179 °F	ASTM D92

Optical Properties	Metric	English	Comments
Refractive Index	1.4681	1.4681	

Descriptive Properties	Value	Comments
Aniline Point °F	207	
Aromatics, by HPLC, %	<1	
Carbon Type by n-d-m, % Naphthenic	39	
Carbon Type by n-d-m, %Aromatic	0	
Carbon Type by n-d-m, %Paraffinic	61	
Color	+25, Saybolt	
Saturates, by HPLC, %	>99	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China