

## ChevronTexaco Pinnacle® EP 320

Category : Fluid , Lubricant

### Material Notes:

Texaco Pinnacle EP oils deliver value through:Excellent thermal and oxidation stability — The synthetic hydrocarbon base oils used in these products provide outstanding stability resulting in longer lubricant and equipment life.High viscosity index and low pour point — These result in very broad operating temperature ranges -46°C to 149°C (-50°F to 300°F) when compared with conventional mineral oil based lubricants.Energy savings — The synthetic base oil will typically increase gear efficiency, resulting in less power consumption.Extended drain intervals — Longer lubricant life, reduced maintenance costs, and less used oil disposal when compared to mineral oil products.Texaco Pinnacle EP oils are high quality industrial EP gear lubricants. They provide excellent load carrying and antiwear properties; protection against rust, corrosion, foaming, and oxidation; and excellent demulsibility resulting in high performance in most types of industrial gearboxes, exemplified by the FZG pass stage of >12. These products possess very high shear stability even under heavily loaded, high speed conditions in industrial gears. The low pour point and very good low temperature fluidity of Texaco Pinnacle EP oils impart improved lubrication during startup at sub-zero temperatures. Their superior viscosity-temperature characteristics provide dependable lubrication at high temperatures. A unique property of the synthetic base oil is a low traction coefficient, resulting in improved gear efficiency, energy savings, less friction, less wear, and lower operating temperatures compared to conventional mineral oil products. Due to the very high viscosity index, these products provide a much higher oil viscosity at operating temperature than a mineral oil product of the same ISO grade. This results in increased oil film thickness and better antiwear protection for both bearings and gears. Texaco Pinnacle EP oils are recommended for all types of enclosed industrial gearboxes: Especially those running continuously at temperatures up to 107°C(225°F) Or exposed to very cold temperatures as low as -46°C(-50°F) Or under severe service conditions, such as heavy loads or low speeds. These products also provide excellent protection for bearings operating under similar conditions. They can be problem-solvers for applications where mineral oil products deteriorate too rapidly or lead to premature failures. Texaco Pinnacle EP oils meet the requirements of: U.S. Steel 224 AGMA 9005 and qualify as AGMA EP gear lubricants Typical test data are average values only. Minor variations which do not affect product performance are to be expected in normal manufacturing. CPS Number: 222081; MSDS Number: 8611

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ChevronTexaco-Pinnacle-EP-320.php](http://www.lookpolymers.com/polymer_ChevronTexaco-Pinnacle-EP-320.php)

Physical Properties	Metric	English	Comments
API Gravity	33.2 °	33.2 °	
Viscosity Measurement	165	165	Viscosity Index
Saybolt Viscosity at 100°F	1570 SUS	1570 SUS	
Saybolt Viscosity at 210°F	174 SUS	174 SUS	
Kinematic Viscosity at 40°C (104°F)	304 cSt	304 cSt	
Kinematic Viscosity at 100°C (212°F)	35.8 cSt	35.8 cSt	

Mechanical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Timken Test Mechanical Properties	36300 g Metric	80.0 lb English	OK Load Comments
--------------------------------------	-------------------	--------------------	---------------------

Thermal Properties	Metric	English	Comments
Pour Point	-39.0 °C	-38.2 °F	
Flash Point	238 °C	460 °F	

Descriptive Properties	Value	Comments
AGMA Grade	6 EP	
FZG Pass Stage	12	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China