

## ChevronTexaco Rykon® 1426 Premium Grease

Category : Fluid , Lubricant , Urea Gellant

### Material Notes:

Chevron Rykon Premium Grease No. 1426 contains polyurea thickener, highly refined paraffinic base oil, rust and oxidation inhibiting additives, as well as heatstable extreme pressure additives. Applications Chevron Rykon Premium Grease No. 1426 is designed to lubricate the constant velocity (CV) joints of front wheel drive cars. It performs under the loads and vibrating motions experienced in the CV joints while being compatible with the various elastomers used as boots for CV joints. This grease can also be used for other applications requiring a high temperature, extreme pressure grease. Chevron Rykon Premium Grease No. 1426 meets the requirements of GM Part No. 7843867

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ChevronTexaco-Rykon-1426-Premium-Grease.php](http://www.lookpolymers.com/polymer_ChevronTexaco-Rykon-1426-Premium-Grease.php)

Physical Properties	Metric	English	Comments
Viscosity Measurement	96	96	Viscosity Index; ASTM D2270
Saybolt Viscosity at 100°F	620 SUS	620 SUS	
Saybolt Viscosity at 210°F	69.5 SUS	69.5 SUS	
Kinematic Viscosity at 40°C (104°F)	118 cSt	118 cSt	ASTM D445
Kinematic Viscosity at 100°C (212°F)	12.5 cSt	12.5 cSt	ASTM D445

Mechanical Properties	Metric	English	Comments
Four Ball Wear	0.600 mm	0.0236 in	
Penetration	312	312	Worked

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	177 °C	351 °F	
Minimum Service Temperature, Air	-40.0 °C	-40.0 °F	
Dropping Point	243 °C	469 °F	

Descriptive Properties	Value	Comments
Bearing Rust	Pass	
Color	Cream	
Texture	Smooth	
Thickener, % / type	11.5 / Polyurea	

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**