

## ChevronTexaco SAE 75W-90 Manual Transaxle Fluid GL-4

Category : Fluid , Lubricant

**Material Notes:**

Features Chevron Manual Transaxle Fluid GL-4 is a multipurpose lubricant. Chevron Manual Transaxle Fluid GL-4 is formulated with ISOSYN® base stocks and synthetic polymer to meet the severe demands of both cold and hot weather operations. It contains a carefully balanced sulfurphosphorus extreme pressure additive package to provide maximum gear protection, long lubricant life, and superior thermal and oxidation stability. In addition, this lubricant is fortified with rust and corrosion inhibitors, a foam inhibitor, and a pour point depressant. Applications Chevron Manual Transaxle Fluid GL-4 is recommended for use in all manual transmissions and manual shift transaxles requiring SAE 75W-90, API GL-4 lubricants. Its multiviscosity characteristics allow smooth shifting over a broad ambient temperature range. Chevron Manual Transaxle Fluid GL-4 meets the performance requirements of API Service Category GL-4.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ChevronTexaco-SAE-75W-90-Manual-Transaxle-Fluid-GL-4.php](http://www.lookpolymers.com/polymer_ChevronTexaco-SAE-75W-90-Manual-Transaxle-Fluid-GL-4.php)

Physical Properties	Metric	English	Comments
API Gravity	29 °	29 °	
Brookfield Viscosity	40000 cP @Temperature -40.0 °C	40000 cP @Temperature -40.0 °F	
Viscosity Measurement	195	195	Viscosity Index; ASTM D2270
Saybolt Viscosity at 100°F	650 SUS	650 SUS	
Saybolt Viscosity at 210°F	107 SUS	107 SUS	
Kinematic Viscosity at 40°C (104°F)	128.3 cSt	128.3 cSt	ASTM D445
Kinematic Viscosity at 100°C (212°F)	21.5 cSt	21.5 cSt	ASTM D445

Thermal Properties	Metric	English	Comments
Pour Point	-42.0 °C	-43.6 °F	ASTM D97

### Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China