

ChevronTexaco Texclad® 2

Category : Fluid , Lubricant , Calcium Gellant

Material Notes:

Texaco Texclad 2 delivers value through: Water tolerance – Resists washout, even when subject to gross water contamination. Excellent adhesiveness – Assures good film strength even in a wet environment. Texaco Texclad 2 is calcium-based grease, which contains special functional fillers such as molybdenum disulfide and graphite, which impart a long-lasting film on working surfaces. Texclad has good load carrying capability and is very resistant to water washout. Texaco Texclad 2 additive system includes friction modifiers such as molybdenum disulfide and graphite, which apply a long lasting antiwear film on lubricated surfaces. Texaco Texclad 2 is recommended: For ball mill gears, traveling water screens, and fork lifts. For chain and sprocket lubrication and as a tenacious fifth wheel lubricant. Typical test data are average values only. Minor variations which do not affect product performance are to be expected in normal manufacturing. Notes: Minimum operating temperature is the lowest temperature at which a grease, already in place, could be expected to provide lubrication. Most greases cannot be pumped at these minimum temperatures. Maximum operating temperature is the highest temperature at which the grease could be used with frequent (daily) relubrication. Determined on mineral oil extracted by vacuum filtration. CPS Number: 221956; MSDS Number: 9008

Order this product through the following link:

http://www.lookpolymers.com/polymer_ChevronTexaco-Texclad-2.php

| Physical Properties | Metric | English | Comments |
|--------------------------------------|----------|----------|-------------|
| Kinematic Viscosity at 40°C (104°F) | 875 cSt | 875 cSt | See Note 3. |
| Kinematic Viscosity at 100°C (212°F) | 36.5 cSt | 36.5 cSt | See Note 3. |

| Mechanical Properties | Metric | English | Comments |
|----------------------------|--------|---------|-------------------------------------|
| Penetration P(60), 1/10 mm | 280 | 280 | Unknown Amount of Work, 25°C (77°F) |

| Thermal Properties | Metric | English | Comments |
|----------------------------------|----------|-----------|-------------|
| Maximum Service Temperature, Air | 79.0 °C | 174 °F | See Note 2. |
| Minimum Service Temperature, Air | -18.0 °C | -0.400 °F | See Note 1. |
| Dropping Point | 232 °C | 450 °F | |

| Descriptive Properties | Value | Comments |
|------------------------|-------|----------|
| Color | Black | |
| Texture | Tacky | |
| Thickener, % | 9 | Calcium |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China