

Chicago Extruded Metals UNS C33500 Copper-Zinc-Lead Alloy

Category : Metal , Nonferrous Metal , Copper Alloy , Brass

Material Notes:

Copper-Zinc-Lead Alloy (Leaded Brass) Finished product available in bars. Chicago Extruded Metal temper codes: H01, H02 Information provided by Chicago Extruded Metals

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chicago-Extruded-Metals-UNS-C33500-Copper-Zinc-Lead-Alloy.php

Physical Properties	Metric	English	Comments
Density	8.47 g/cc	0.306 lb/in ³	

Mechanical Properties	Metric	English	Comments
Tensile Strength	276 - 552 MPa	40000 - 80000 psi	
Tensile Strength, Yield	103 - 172 MPa	15000 - 25000 psi	
Elongation at Break	7.0 - 65 %	7.0 - 65 %	
Machinability	60 %	60 %	UNS C36000 (free-cutting brass) = 100%

Thermal Properties	Metric	English	Comments
Thermal Conductivity	116 W/m-K	804 BTU-in/hr-ft ² -°F	

Component Elements Properties	Metric	English	Comments
Copper, Cu	62 - 65 %	62 - 65 %	
Iron, Fe	0.15 %	0.15 %	
Lead, Pb	0.25 - 0.70 %	0.25 - 0.70 %	
Other, total	0.40 %	0.40 %	
Zinc, Zn	33.75 - 37.2 %	33.75 - 37.2 %	as balance

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00000663 ohm-cm	0.00000663 ohm-cm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China