

China-Yixing Longly Refractories 95 Alumina Ceramic Tubes & Rods

Category: Ceramic, Oxide, Aluminum Oxide

Material Notes:

LONGLY's alumina ceramic tubes and rods (the tolerances of +/- 0.02mm could be reached by mechanical or electronic finishing or mirror surface finishing) have high hardness, wear resistance, insulation and high temperature resistance. Alumina ceramic tubes are mainly applicable to the material conveying with wear resistant and heavy scouring resistant demands, such as material conveying pipelines for coal-fired power generation, metallurgical and geological industries. Meanwhile they can be used as fuse insulating tube on the electric and electronic appliances. Alumina ceramic rods are used as resistor's ceramic matrix and ceramic top pillar on two-metal thermostat. Information Provided by China Yixing Longly Refractories Co. Ltd

Order this product through the following link:

http://www.lookpolymers.com/polymer_China-Yixing-Longly-Refractories-95-Alumina-Ceramic-Tubes-Rods.php

Physical Properties	Metric	English	Comments
Bulk Density	3.55 - 3.65 g/cc	0.128 - 0.132 lb/in ³	
Water Absorption	<= 0.050 %	<= 0.050 %	

Mechanical Properties	Metric	English	Comments
Hardness, Mohs	9.0	9.0	
Flexural Strength	>= 520 MPa	>= 75400 psi	cold bending
Compressive Strength	>= 500 MPa	>= 72500 psi	Ambient

Thermal Properties	Metric	English	Comments
6.20 - 7.60 μm/m-°C CTE, linear @Temperature 25.0 - 800 °C	6.20 - 7.60 μm/m-°C	3.44 - 4.22 μin/in-°F	
	· .	@Temperature 77.0 - 1470 °F	
Thermal Conductivity	21.0 W/m-K	146 BTU-in/hr-ft ² -°F	
Maximum Service Temperature, Air	>= 1500 °C	>= 2730 °F	

Component Elements Properties	Metric	English	Comments
Al203	92 - 96.5 %	92 - 96.5 %	

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	
	@Temperature 100 °C	@Temperature 212 °F	
Dielectric Strength	15.0 kV/mm	381 kV/in	Insulating Strength



Electrical Properties	Metric 20.3 kV/mm	English (V/in	Comments Sec. Dreamdown Strength
Descriptive Properties		Value	Comments
Refractoriness (°C)		>2000	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China