

Chosun Refractories 1000BOARD Board

Category : Ceramic

Material Notes:

Information provided by Chosun Refractories via Korea Institute of Ceramic Engineering and Technology (KICET).

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chosun-Refractories-1000BOARD-Board.php

Physical Properties	Metric	English	Comments
Bulk Density	0.250 g/cc	0.00903 lb/in ³	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	1100 °C	2010 °F	
Shrinkage	0.30 %	0.30 %	
	@Temperature 800 °C, Time 86400 sec	@Temperature 1470 °F, Time 24.0 hour	
	1.3 %	1.3 %	
	@Temperature 900 °C, Time 86400 sec	@Temperature 1650 °F, Time 24.0 hour	
	2.0 %	2.0 %	
	@Temperature 1000 °C, Time 86400 sec	@Temperature 1830 °F, Time 24.0 hour	

Component Elements Properties	Metric	English	Comments
Loss on Ignition(%)	6.5 %	6.5 %	

Descriptive Properties	Value	Comments
Typical applications	high temp. furnace linings, elec.furnace lining back-up, fire protection	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China