

Chosun Refractories 1400BULK Bulk

Category : Ceramic

Material Notes:

Information provided by Chosun Refractories via Korea Institute of Ceramic Engineering and Technology (KICET).

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chosun-Refractories-1400BULK-Bulk.php

Thermal Properties	Metric	English	Comments
Melting Point	1760 °C	3200 °F	
Maximum Service Temperature, Air	1430 °C	2610 °F	

Component Elements Properties	Metric	English	Comments
Al2O3	35 %	35 %	
SiO2	49.7 %	49.7 %	
ZrO2	15 %	15 %	

Descriptive Properties	Value	Comments
Pack Density, vibrating part pack density (kg/m ³)	250	
Pack Density,normal pack density(kg/?)	60~250	
Packaging	10kg Carton Box	
Typical applications	furnace roof, back-up insulation packing, expansion joint filler, various composites, Asbestos paper substitutes	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China