

Chosun Refractories 1500 ACE BLANKET Blanket

Category : Ceramic , Oxide , Silicon Oxide

Material Notes:

Information provided by Chosun Refractories via Korea Institute of Ceramic Engineering and Technology (KICET).

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chosun-Refractories-1500-ACE-BLANKET-Blanket.php

Thermal Properties	Metric	English	Comments
Melting Point	1760 °C	3200 °F	
Maximum Service Temperature, Air	1500 °C	2730 °F	
Shrinkage	1.5 %	1.5 %	
	@Temperature 1200 °C, Time 86400 sec	@Temperature 2190 °F, Time 24.0 hour	
	1.6 %	1.6 %	
	@Temperature 1300 °C, Time 86400 sec	@Temperature 2370 °F, Time 24.0 hour	
	2.0 %	2.0 %	
	@Temperature 1400 °C, Time 86400 sec	@Temperature 2550 °F, Time 24.0 hour	

Component Elements Properties	Metric	English	Comments
Al2O3	40 %	40 %	
Cr2O3	1.8 %	1.8 %	
SiO2	58.1 %	58.1 %	

Descriptive Properties	Value	Comments
Typical applications	Furnace Linings, Heat seals, Packing, Fire Protection, Noise reduction, Filter Material	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China