

Chosun Refractories 1600BLANKET Blanket

Category : Ceramic , Oxide , Aluminum Oxide

Material Notes:

Information provided by Chosun Refractories via Korea Institute of Ceramic Engineering and Technology (KICET).

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chosun-Refractories-1600BLANKET-Blanket.php

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	1600 °C	2910 °F	
Shrinkage	0.50 %	0.50 %	
	@Temperature 1500 °C, Time 86400 sec	@Temperature 2730 °F, Time 24.0 hour	
	0.60 %	0.60 %	
	@Temperature 1400 °C, Time 86400 sec	@Temperature 2550 °F, Time 24.0 hour	

Component Elements Properties	Metric	English	Comments
Al2O3	72 %	72 %	
SiO2	28 %	28 %	

Descriptive Properties	Value	Comments
Typical applications	Furnace Linings, Heat seals, Packing, Fire Protection, Noise reduction, Filter Material	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China