

Chosun Refractories A65 Special High-Density Gunning Castable

Category : Ceramic , Oxide , Aluminum Oxide

Material Notes:

Information provided by Chosun Refractories via Korea Institute of Ceramic Engineering and Technology (KICET).

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chosun-Refractories-A65-Special-High-Density-Gunning-Castable.php

Physical Properties	Metric	English	Comments
Bulk Density	2.66 g/cc	0.0961 lb/in ³	
	@Temperature 1000 °C, Time 10800 sec	@Temperature 1830 °F, Time 3.00 hour	
	2.66 g/cc	0.0961 lb/in ³	
	@Temperature 1500 °C, Time 10800 sec	@Temperature 2730 °F, Time 3.00 hour	
	2.69 g/cc	0.0972 lb/in ³	
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
Porosity	19.5 %	19.5 %	
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
	24 %	24 %	
	@Temperature 1500 °C, Time 10800 sec	@Temperature 2730 °F, Time 3.00 hour	
	24.5 %	24.5 %	
	@Temperature 1000 °C, Time 10800 sec	@Temperature 1830 °F, Time 3.00 hour	

Mechanical Properties	Metric	English	Comments
Modulus of Rupture	0.0034335 GPa	0.49799 ksi	
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
	0.003924 GPa	0.5691 ksi	
	@Temperature 1000 °C, Time 10800 sec	@Temperature 1830 °F, Time 3.00 hour	
	0.003924 GPa	0.5691 ksi	
	@Temperature 1500 °C, Time 10800 sec	@Temperature 2730 °F, Time 3.00 hour	

Thermal Properties	Metric	English	Comments
Shrinkage	-0.0600 %	-0.0600 %	
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
	-0.0600 %	-0.0600 %	
	@Temperature 1000 °C, Time 10800 sec	@Temperature 1830 °F, Time 3.00 hour	
	0.050 %	0.050 %	
	@Temperature 1500 °C, Time 10800 sec	@Temperature 2730 °F, Time 3.00 hour	

Component Elements Properties	Metric	English	Comments
Al2O3	65 %	65 %	
SiC	30 %	30 %	
SiO2	1.0 %	1.0 %	

Descriptive Properties	Value	Comments
Main Applications	Blast furnace Main runner	
Material Required for Estimating (kg/?)	2,700	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China