

Chosun Refractories AN-210 Blast Furnace Runner Refractory

Category : Ceramic , Oxide , Aluminum Oxide

Material Notes:

Information provided by Chosun Refractories via Korea Institute of Ceramic Engineering and Technology (KICET).

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chosun-Refractories-AN-210-Blast-Furnace-Runner-Refractory.php

Physical Properties	Metric	English	Comments
Bulk Density	2.31 g/cc	0.0835 lb/in ³	
	@Temperature 1500 °C, Time 10800 sec	@Temperature 2730 °F, Time 3.00 hour	
	2.52 g/cc	0.0910 lb/in ³	
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Compressive Strength	14.7 MPa	2130 psi	
	@Temperature 1500 °C, Time 10800 sec	@Temperature 2730 °F, Time 3.00 hour	Cold Crushing Strength
	19.6 MPa	2840 psi	
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	Cold Crushing Strength

Thermal Properties	Metric	English	Comments
Shrinkage	-1.50 %	-1.50 %	
	@Temperature 1500 °C, Time 7200 sec	@Temperature 2730 °F, Time 2.00 hour	

Component Elements Properties	Metric	English	Comments
Al2O3	54 %	54 %	
SiO2	16 %	16 %	

Descriptive Properties	Value	Comments
Chemical Analysis(%),SiC+C	23	
Installation Method	Ramming	
Main Applications	Min runner	

Material Required for Estimating (kg/?) Descriptive Properties	2.600 Value	Comments
---	----------------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China