

Chosun Refractories APC-1 Special Mortar

Category : Ceramic

Material Notes:

Information provided by Chosun Refractories via Korea Institute of Ceramic Engineering and Technology (KICET).

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chosun-Refractories-APC-1-Special-Mortar.php

Mechanical Properties	Metric	English	Comments
Adhesive Bond Strength	0.981 MPa @Temperature 110 °C, Time 86400 sec	142 psi @Temperature 230 °F, Time 24.0 hour	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	100 °C	212 °F	

Processing Properties	Metric	English	Comments
Cure Time	20.0 - 40.0 min	0.333 - 0.667 hour	Setting Time

Descriptive Properties	Value	Comments
Chemical Analysis(%) at 500?	50=	
Main Applications	For Acid-proof Bricks	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China