

Chosun Refractories B-6 Insulating Firebrick

Category : Ceramic

Material Notes:

Information provided by Chosun Refractories via Korea Institute of Ceramic Engineering and Technology (KICET).

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chosun-Refractories-B-6-Insulating-Firebrick.php

| Physical Properties | Metric | English | Comments |
|---------------------|-------------------|----------------------------------|----------|
| Bulk Density | ≥ 0.900 g/cc | ≥ 0.0325 lb/in ³ | |

| Mechanical Properties | Metric | English | Comments |
|-----------------------|-----------------|----------------|------------------------|
| Compressive Strength | ≤ 2.94 MPa | ≤ 427 psi | Cold Crushing Strength |

| Thermal Properties | Metric | English | Comments |
|----------------------|--|---|----------|
| Thermal Conductivity | ≥ 0.3141 W/m-K @Temperature 350 °C | ≥ 2.176 BTU-in/hr- ft ² -°F @Temperature 662 °F | |

| Descriptive Properties | Value | Comments |
|---|-------|----------|
| Temp.(?) Reheating Shrinkage less than 2.0% | 1,400 | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China