

Chosun Refractories CRS-A60 Blast Furnace Tap-Hole Refractory

Category : Ceramic , Oxide , Aluminum Oxide

Material Notes:

Information provided by Chosun Refractories via Korea Institute of Ceramic Engineering and Technology (KICET).

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chosun-Refractories-CRS-A60-Blast-Furnace-Tap-Hole-Refractory.php

Physical Properties	Metric	English	Comments
Bulk Density	2.26 g/cc	0.0816 lb/in ³	
Porosity	30 %	30 %	

Mechanical Properties	Metric	English	Comments
Compressive Strength	17.2 MPa @Temperature 1350 °C, Time 10800 sec	2490 psi @Temperature 2460 °F, Time 3.00 hour	Cold Crushing Strength

Thermal Properties	Metric	English	Comments
Shrinkage	0.00 % @Temperature 1350 °C, Time 10800 sec	0.00 % @Temperature 2460 °F, Time 3.00 hour	

Component Elements Properties	Metric	English	Comments
Al2O3	59 %	59 %	
SiO2	13 %	13 %	

Descriptive Properties	Value	Comments
Chemical Analysis(%),Si3N4	5.6	
Chemical Analysis(%),SiC+C	19	
Main Applications	Corex	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China