

Chosun Refractories CTC-60TD Monolithic Refractories for Ladle and Tundish

Category : Ceramic , Oxide , Aluminum Oxide

Material Notes:

Information provided by Chosun Refractories via Korea Institute of Ceramic Engineering and Technology (KICET).

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chosun-Refractories-CTC-60TD-Monolithic-Refractories-for-Ladle-and-Tundish.php

Mechanical Properties	Metric	English	Comments
Modulus of Rupture	0.002943 GPa	0.4269 ksi	
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
	0.008829 GPa	1.281 ksi	
	@Temperature 1500 °C, Time 10800 sec	@Temperature 2730 °F, Time 3.00 hour	
Compressive Strength	19.6 MPa	2840 psi	Cold Crushing Strength
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
	39.2 MPa	5690 psi	Cold Crushing Strength
	@Temperature 1500 °C, Time 10800 sec	@Temperature 2730 °F, Time 3.00 hour	

Thermal Properties	Metric	English	Comments
Shrinkage	0.00 %	0.00 %	
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
	1.75 %	1.75 %	
	@Temperature 1500 °C, Time 10800 sec	@Temperature 2730 °F, Time 3.00 hour	

Component Elements Properties	Metric	English	Comments
Al2O3	61 %	61 %	
SiO2	34 %	34 %	

Descriptive Properties	Value	Comments
Installation Method	Casting, Vibrating	
Main Applications	Tundish	

Material Required for Estimating (kg/?) Descriptive Properties	2.500 Value	Comments
Water Required for Casting(%)	7.1	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China