

Chosun Refractories H-4 High Alumina brick

Category : Ceramic , Oxide , Aluminum Oxide

Material Notes:

Information provided by Chosun Refractories via Korea Institute of Ceramic Engineering and Technology (KICET).

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chosun-Refractories-H-4-High-Alumina-brick.php

Physical Properties	Metric	English	Comments
Bulk Density	2.28 g/cc	0.0824 lb/in ³	
Porosity	20 %	20 %	

Mechanical Properties	Metric	English	Comments
Compressive Strength	39.2 MPa	5690 psi	Cold Crushing Strength

Thermal Properties	Metric	English	Comments
CTE, linear	5.00 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	2.78 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	
	@Temperature 1000 $^\circ\text{C}$	@Temperature 1830 $^\circ\text{F}$	
Shrinkage	-0.500 - 0.50 %	-0.500 - 0.50 %	
	@Temperature 1400 $^\circ\text{C}$, Time 7200 sec	@Temperature 2550 $^\circ\text{F}$, Time 2.00 hour	

Component Elements Properties	Metric	English	Comments
Al ₂ O ₃	48 %	48 %	
Fe ₂ O ₃	1.6 %	1.6 %	

Descriptive Properties	Value	Comments
Main Application	Resistance to Spalling	
Refractories Under Load(2kg/?,T2?)	1,450	
Refractoriness (SK)	35=	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China