

## Chosun Refractories HSC-16 Dense and High-Strength Castable, Credens

Category : Ceramic , Oxide , Aluminum Oxide

### Material Notes:

Information provided by Chosun Refractories via Korea Institute of Ceramic Engineering and Technology (KICET).

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Chosun-Refractories-HSC-16-Dense-and-High-Strength-Castable-Credens.php](http://www.lookpolymers.com/polymer_Chosun-Refractories-HSC-16-Dense-and-High-Strength-Castable-Credens.php)

Mechanical Properties	Metric	English	Comments
Modulus of Rupture	0.00981 GPa	1.42 ksi	
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
	0.010791 GPa	1.5651 ksi	
	@Temperature 1000 °C, Time 10800 sec	@Temperature 1830 °F, Time 3.00 hour	
	0.011772 GPa	1.7074 ksi	
	@Temperature 1500 °C, Time 10800 sec	@Temperature 2730 °F, Time 3.00 hour	
Compressive Strength	59.8 MPa	8680 psi	Cold Crushing Strength
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
	61.8 MPa	8960 psi	Cold Crushing Strength
	@Temperature 1000 °C, Time 10800 sec	@Temperature 1830 °F, Time 3.00 hour	
	65.7 MPa	9530 psi	Cold Crushing Strength
	@Temperature 1500 °C, Time 10800 sec	@Temperature 2730 °F, Time 3.00 hour	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	1600 °C	2910 °F	limited
Shrinkage	-0.500 %	-0.500 %	
	@Temperature 1500 °C, Time 10800 sec	@Temperature 2730 °F, Time 3.00 hour	
	-0.0400 %	-0.0400 %	
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	

Component Elements Properties	Metric	English	Comments

Al2O3 Component Elements Properties	55 % Metric	55 % English	Comments
CaO	2.0 %	2.0 %	
SiO2	40 %	40 %	

Processing Properties	Metric	English	Comments
Cure Time	120 - 600 min	2.00 - 10.0 hour	Setting Time

Descriptive Properties	Value	Comments
Installation Method	Vibrating, Casting	
Material Required for Estimating(kg/?)	2,600	
Water Required for Casting(%)	7	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China