

## Chosun Refractories HSC-85AL Dense and High-Strength Castable, Credens

Category : Ceramic , Oxide , Aluminum Oxide

### Material Notes:

Information provided by Chosun Refractories via Korea Institute of Ceramic Engineering and Technology (KICET).

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Chosun-Refractories-HSC-85AL-Dense-and-High-Strength-Castable-Credens.php](http://www.lookpolymers.com/polymer_Chosun-Refractories-HSC-85AL-Dense-and-High-Strength-Castable-Credens.php)

Mechanical Properties	Metric	English	Comments
Modulus of Rupture	0.00981 GPa	1.42 ksi	
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
	0.011772 GPa	1.7074 ksi	
	@Temperature 1000 °C, Time 10800 sec	@Temperature 1830 °F, Time 3.00 hour	
Compressive Strength	52.0 MPa	7540 psi	Cold Crushing Strength
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
	66.7 MPa	9670 psi	Cold Crushing Strength
	@Temperature 1000 °C, Time 10800 sec	@Temperature 1830 °F, Time 3.00 hour	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	1700 °C	3090 °F	limited
Shrinkage	-0.0300 %	-0.0300 %	
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	

Component Elements Properties	Metric	English	Comments
Al2O3	85 %	85 %	
SiO2	8.0 %	8.0 %	

Processing Properties	Metric	English	Comments
Cure Time	120 - 600 min	2.00 - 10.0 hour	Setting Time

Descriptive Properties	Value	Comments
Installation Method	Vibrating, Casting	

Material Required for Estimating(kg/?) Descriptive Properties	2.900 Value	Comments
Water Required for Casting(%)	5.5	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China