

Chosun Refractories INCT-120S Light-Weight Castable

Category : Ceramic

Material Notes:

Information provided by Chosun Refractories via Korea Institute of Ceramic Engineering and Technology (KICET).

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chosun-Refractories-INCT-120S-Light-Weight-Castable.php

Mechanical Properties	Metric	English	Comments
Modulus of Rupture	2.41e-7 - 0.000491 GPa	0.0000349 - 0.0711 ksi	
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
	0.0004905 - 0.0024525 GPa	0.07114 - 0.35571 ksi	
	@Temperature 500 °C, Time 10800 sec	@Temperature 932 °F, Time 3.00 hour	
	0.0014715 - 0.0034335 GPa	0.21343 - 0.49799 ksi	
	@Temperature 1000 °C, Time 10800 sec	@Temperature 1830 °F, Time 3.00 hour	
Compressive Strength	2.94 - 7.85 MPa	427 - 1140 psi	Cold Crushing Strength
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
	2.94 - 7.85 MPa	427 - 1140 psi	Cold Crushing Strength
	@Temperature 500 °C, Time 10800 sec	@Temperature 932 °F, Time 3.00 hour	
	2.94 - 7.85 MPa	427 - 1140 psi	Cold Crushing Strength
	@Temperature 1000 °C, Time 10800 sec	@Temperature 1830 °F, Time 3.00 hour	

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.233 W/m-K	1.61 BTU-in/hr-ft ² -°F	
	@Temperature 260 °C	@Temperature 500 °F	
	0.2792 W/m-K	1.934 BTU-in/hr-ft ² -°F	
	@Temperature 540 °C	@Temperature 1000 °F	
	0.3257 W/m-K	2.257 BTU-in/hr-ft ² -°F	
	@Temperature 800 °C	@Temperature 1470 °F	
Maximum Service Temperature, Air			limited

Thermal Properties	1200 °C Metric	2190 °F English	Comments
Shrinkage	-0.350 %	-0.350 %	
	@Temperature 1000 °C, Time 10800 sec	@Temperature 1830 °F, Time 3.00 hour	
	-0.0600 %	-0.0600 %	
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	

Component Elements Properties	Metric	English	Comments
Al2O3	33 %	33 %	
SiO2	43 %	43 %	

Descriptive Properties	Value	Comments
Installation Method	Casting, Troweling	
Main Applications	High temperature Low thermal conductivity	
Material Required for Estimating (kg/?)	900	
Water Required for Casting(%)	40-50	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China