

Chosun Refractories PT-170 Plastic Refractory

Category : Ceramic , Oxide , Aluminum Oxide

Material Notes:

Information provided by Chosun Refractories via Korea Institute of Ceramic Engineering and Technology (KICET).

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chosun-Refractories-PT-170-Plastic-Refractory.php

Mechanical Properties	Metric	English	Comments
Modulus of Rupture	3.85e-7 - 0.000981 GPa	0.0000558 - 0.142 ksi	
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
	0.002943 - 0.005886 GPa	0.4269 - 0.8537 ksi	
	@Temperature 1350 °C, Time 10800 sec	@Temperature 2460 °F, Time 3.00 hour	
	0.0034335 - 0.0063765 GPa	0.49799 - 0.92485 ksi	
	@Temperature 1500 °C, Time 10800 sec	@Temperature 2730 °F, Time 3.00 hour	
Compressive Strength	4.90 - 9.81 MPa	711 - 1420 psi	Cold Crushing Strength
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
	14.7 - 24.5 MPa	2130 - 3560 psi	Cold Crushing Strength
	@Temperature 1350 °C, Time 10800 sec	@Temperature 2460 °F, Time 3.00 hour	
	19.6 - 29.4 MPa	2840 - 4270 psi	Cold Crushing Strength
	@Temperature 1500 °C, Time 10800 sec	@Temperature 2730 °F, Time 3.00 hour	

Thermal Properties	Metric	English	Comments
Thermal Conductivity	1.0236 W/m-K	7.0921 BTU-in/hr- ft ² -°F	
	@Temperature 500 °C	@Temperature 932 °F	
	1.1399 W/m-K	7.8980 BTU-in/hr- ft ² -°F	
	@Temperature 1000 °C	@Temperature 1830 °F	
Maximum Service Temperature, Air	1700 °C	3090 °F	limited
	-0.900 %	-0.900 %	

Thermal Properties	Metric	English	Comments
	@Temperature 1500 °C, Time 10800 sec	@Temperature 2730 °F, Time 3.00 hour	
	-0.600 %	-0.600 %	
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
	-0.100 %	-0.100 %	
	@Temperature 1350 °C, Time 10800 sec	@Temperature 2460 °F, Time 3.00 hour	

Component Elements Properties	Metric	English	Comments
Al2O3	63 %	63 %	
SiO2	32 %	32 %	

Descriptive Properties	Value	Comments
Main Applications	Various furnace	
Material Required for Estimating (kg/?)	2,500	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China