

## Chosun Refractories SAL70 Special Alumina brick

Category : Ceramic , Oxide , Aluminum Oxide

**Material Notes:**

Information provided by Chosun Refractories via Korea Institute of Ceramic Engineering and Technology (KICET).

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Chosun-Refractories-SAL70-Special-Alumina-brick.php](http://www.lookpolymers.com/polymer_Chosun-Refractories-SAL70-Special-Alumina-brick.php)

Physical Properties	Metric	English	Comments
Bulk Density	2.65 g/cc	0.0957 lb/in <sup>3</sup>	
Porosity	18 %	18 %	

Mechanical Properties	Metric	English	Comments
Compressive Strength	68.6 MPa	9960 psi	Cold Crushing Strength

Thermal Properties	Metric	English	Comments
CTE, linear	5.50 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	3.06 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	
	@Temperature 1000 °C	@Temperature 1830 °F	
Shrinkage	-0.300 - 0.30 %	-0.300 - 0.30 %	
	@Temperature 1600 °C, Time 7200 sec	@Temperature 2910 °F, Time 2.00 hour	

Component Elements Properties	Metric	English	Comments
Al <sub>2</sub> O <sub>3</sub>	72 %	72 %	
Fe <sub>2</sub> O <sub>3</sub>	1.2 %	1.2 %	

Descriptive Properties	Value	Comments
Main Application	Lime Kiln, Cement Kiln, Various Rotary Kiln, Reheating furnace, Soaking Pits, Various furnace	
Refractories Under Load(2kg/?,T2?)	1,600	
Refractoriness (SK)	38	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China