

Chosun Refractories SB50 Bricks, Oxide Bonded SiC

Category : Ceramic , Carbide

Material Notes:

Information provided by Chosun Refractories via Korea Institute of Ceramic Engineering and Technology (KICET).

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chosun-Refractories-SB50-Bricks-Oxide-Bonded-SiC.php

Physical Properties	Metric	English	Comments
Bulk Density	2.60 g/cc	0.0939 lb/in ³	
Porosity	15 %	15 %	

Mechanical Properties	Metric	English	Comments
Modulus of Rupture	0.01962 GPa	2.846 ksi	
	@Temperature 1400 °C	@Temperature 2550 °F	
Compressive Strength	0.024525 GPa	3.5571 ksi	
	@Temperature 250 °C	@Temperature 482 °F	
Compressive Strength	58.8 MPa	8530 psi	Cold Crushing Strength

Thermal Properties	Metric	English	Comments
CTE, linear	5.20 μm/m-°C	2.89 μin/in-°F	
	@Temperature 1000 °C	@Temperature 1830 °F	

Component Elements Properties	Metric	English	Comments
Fe2O3	0.80 %	0.80 %	
SiC	51 %	51 %	

Descriptive Properties	Value	Comments
Refractories Under Load(2kg/?,T2?)	1,600	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China