

Chosun Refractories SCX-16KL Special SiC Castable

Category : Ceramic , Carbide , Oxide , Aluminum Oxide

Material Notes:

Information provided by Chosun Refractories via Korea Institute of Ceramic Engineering and Technology (KICET).

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chosun-Refractories-SCX-16KL-Special-SiC-Castable.php

Mechanical Properties	Metric	English	Comments
Compressive Strength	39.2 MPa	5690 psi	Cold Crushing Strength
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
	88.3 MPa	12800 psi	Cold Crushing Strength
	@Temperature 1400 °C, Time 10800 sec	@Temperature 2550 °F, Time 3.00 hour	

Thermal Properties	Metric	English	Comments
Shrinkage	-0.300 %	-0.300 %	
	@Temperature 1400 °C, Time 10800 sec	@Temperature 2550 °F, Time 3.00 hour	
	0.00 %	0.00 %	
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	

Component Elements Properties	Metric	English	Comments
Al2O3	53 %	53 %	
SiC	16 %	16 %	

Descriptive Properties	Value	Comments
Installation Method	Casting, Vibrating	
Material Required for Estimating (kg/?)	2,400	
Water Required for Casting(%)	7.5	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China