

Chosun Refractories SF34 Hard Fireclay brick

Category : Ceramic

Material Notes:

Information provided by Chosun Refractories via Korea Institute of Ceramic Engineering and Technology (KICET).

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chosun-Refractories-SF34-Hard-Fireclay-brick.php

Physical Properties	Metric	English	Comments
Bulk Density	2.32 g/cc	0.0838 lb/in ³	
Porosity	15 %	15 %	

Mechanical Properties	Metric	English	Comments
Compressive Strength	63.7 MPa	9250 psi	Cold Crushing Strength

Thermal Properties	Metric	English	Comments
CTE, linear	5.60 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	3.11 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	
	@Temperature 1000 °C	@Temperature 1830 °F	
Shrinkage	-0.200 - 0.20 %	-0.200 - 0.20 %	
	@Temperature 1500 °C, Time 7200 sec	@Temperature 2730 °F, Time 2.00 hour	

Component Elements Properties	Metric	English	Comments
Al ₂ O ₃	43 %	43 %	
Fe ₂ O ₃	1.2 %	1.2 %	

Descriptive Properties	Value	Comments
Quality	Anti-abrasion, Anti-spalling, Anti-corrosion	
Refractories Under Load(2kg/?,T2?)	1,500	
Refractoriness (SK)	34	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China