

Chosun Refractories SF35 Hard Fireclay brick

Category : Ceramic

Material Notes:

Information provided by Chosun Refractories via Korea Institute of Ceramic Engineering and Technology (KICET).

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chosun-Refractories-SF35-Hard-Fireclay-brick.php

Physical Properties	Metric	English	Comments
Bulk Density	2.33 g/cc	0.0842 lb/in ³	
Porosity	13 %	13 %	

Mechanical Properties	Metric	English	Comments
Compressive Strength	68.6 MPa	9960 psi	Cold Crushing Strength

Thermal Properties	Metric	English	Comments
CTE, linear	5.80 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	3.22 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	
	@Temperature 1000 $^\circ\text{C}$	@Temperature 1830 $^\circ\text{F}$	
Shrinkage	-0.200 - 0.20 %	-0.200 - 0.20 %	
	@Temperature 1500 $^\circ\text{C}$, Time 7200 sec	@Temperature 2730 $^\circ\text{F}$, Time 2.00 hour	

Component Elements Properties	Metric	English	Comments
Al ₂ O ₃	46 %	46 %	
Fe ₂ O ₃	1.2 %	1.2 %	

Descriptive Properties	Value	Comments
Quality	Anti-abrasion, Anti-spalling, Anti-corrosion	
Refractories Under Load(2kg/?,T2?)	1,500	
Refractoriness (SK)	35	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China